

 $\label{lem:condition} \mbox{Decorative solution for use around walkways, patios and gardens.}$ 











## **INSTALLATION GUIDELINES: SAND**


**Compacted Aggregate** 

After excavation, compact the sub grade and install a woven separation fabric if needed. Spread and compact a base of clean, dense graded aggregate (road base). Typical compacted base thickness is 4-6" for pedestrian applications. Pavers are set on a loosely screened 1" bed of graded, clean concrete sand. Maintain a joint size of 1/16" – 3/16". When pavers are set, compact paving stones into sand with mechanical plate vibrator. Joint sand may be spread over paving stones during compaction. Installed pavers should be set 1/8" to 1/4" above final elevations to compensate for any potential settlement. Spread clean dry sand over surface and broom sweep to fill joints. Run vibrator one final time after filling joints.

## 2% Modified Neoprene Adhesive 3/4" Bituminous Setting Bed Concrete Asphalt or

NICOLOCK PAVING STONE 1"- 3 1/8" THICK

## **CROSS-SECTION OF TYPICAL INSTALLATION**



**NOTE:** All measurements are nominal. Variance in square footage or linear footage coverage can be up to 5% depending on joint width. The possible occurrence of efflorescence does not affect the structural integrity of the product. Efflorescence is a normal occurrence in concrete products and will dissipate with normal weathering. The use of concrete as a base or setting bed may increase the possibility of efflorescence.

**Compacted Sub-Base**